

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
22 January 2004 (22.01.2004)

PCT

(10) International Publication Number
WO 2004/007785 A1

(51) International Patent Classification⁷: **C22C 38/04**

(21) International Application Number:
PCT/KR2003/001302

(22) International Filing Date: 3 July 2003 (03.07.2003)

(25) Filing Language: Korean

(26) Publication Language: English

(30) Priority Data:
10-2002-0040253 11 July 2002 (11.07.2002) KR

(71) Applicant (for all designated States except US):
SAMHWA STEEL CO., LTD. [KR/KR]; 339-4 Samrak-Dong, Sasang-Gu, Pusan 617-825 (KR).

(72) Inventor; and

(75) Inventor/Applicant (for US only): AHN, Soon-Tae [KR/KR]; 339-4 Samrak-Dong, Sasang-Gu, Pusan 617-825 (KR).

(74) Agent: KIM, Young-Hwan; 5th Fl. Chogwang Bldg. 1572-15, Seocho-Dong, Seocho-Gu, Seoul 137-874 (KR).

(81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.


(84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: QUENCHED AND TEMPERED STEEL WIRE WITH SUPERIOR COLD FORGING CHARACTERISTICS.



(57) Abstract: Disclosed is a quenched and tempered steel wire with superior cold forging characteristics, consisting essentially of 0.1-0.5 wt % of C, 1.0 wt % or less of Si, 0.2-2.5 wt % of Mn, 0.03 wt % or less of P, and 0.03 wt % of S, with the balance being Fe and inevitable impurities, which has tensile strength of 700-1300 Mpa and percent spheroidization of carbides of at least 30 %. Such quenched and tempered steel wire, which is subjected to a quenching and tempering processes by high frequency induction heating in a short period, without a spheroidizing annealing process needing a long period, has forging characteristics equal or superior to those of spheroidizing annealed steel wire, thus increasing productivity. Therefore, the quenched and tempered steel wire is applicable to make various bolts and shafts as parts for machine structures requiring high strengths.